PYROLON° CBFR

Advanced Chemical Barrier and Flame Resistance for the Highest Chemical Hold-Out

Pyrolon[®] CBFR Applications

Ammonia Hydrofloric Acid Petrochemical



Heat SealedSeam



Pyrolon CBFR - Advanced chemical protection and self extinguishing FR protection. Designed to be worn over primary FR protective clothing, for environments where both chemical exposures and flash fire are a concern. This advanced chemical barrier is self-extinguishing, won't melt or drip, and meets the NFPA 2113 requirements for section 5.1.9.

Pyrolon CBFR is your choice for protection in harsh chemical environments for the likes of Ammonia, Hydroflouric Acid and other serious chemicals where workers need chemical protection over primary FR protective garments.





Secondary FR and Chemical Protective Garment

Primary FR Protective Garment



Pyrolon[®] CBFR Brand Features:

Combines Advanced Chemical Barrier with Flame Resistance

Higher Chemical Hold-out Than CRFR

Chemical Permeation Data Available

Lower predicted body burn when worn over UL certified NFPA 2112 FR garments

Pyrolon[®] CBFR Configurations





Coverall 52132 • Respirator-fit hood • Storm flap over zipper • Elastic face, wrists and ankles Sizes: S - 5XL

Case Pack: 6

 Respirator-fit hood
 Storm flap over zipper
 Elastic face and wrists
 Attached boots
 Sizes: S - 5XL
 Case Pack: 6

52151

Pyrolon[®] CB-FR Physical Properties Physical Properties

Physical Property	Test Method	Units	Test Results
Basis Weight	ASTM D3776	oz./sq. yd	7.16 oz/y2
Thickness	ASTM D1777	mils	12
Grab Tensile MD	ASTM D5034	lbs.	55.2 lbs.
Grab Tensile XD	ASTM D5034	lbs.	42.88 lbs.
Mullenburst	ASTM D3786	psi	32.5
Trapezoidal Tear MD	ASTM D5587	lbs.	16.28 lbs.
Trapezoidal Tear CD	ASTM D5587	lbs.	24.08 lbs.
Surface Resistance	EN1149	Ω	Pass

Pyrolon® CB-FR Permeation Testing - ASTM F1001

Chemical	CAS	Physical	Concentra-	ASTM F739	EN 369
Acetone	<u>Number</u> 67-64-1	State	<u>tion</u> 99%	>480	>480
Acetonitrile	75-05-8	Liquid	99%	>480	>480
Acrylonitrile	107-13-1	Liquid	99%	>480	>480
Benzene	71-43-2	Liquid	99%	>480	>480
Carbon Disulfide	75-15-0	Liquid	99%	>480	>480
Crude Oil	Various	Liquid	Mixture	58	>480
Dichloromethane	75-09-2	Liquid	99%	>480	>480
Diesel Fuel	Various	Liquid	Mixture	>480	>480
Diethylamine (DEA)	109-89-7		99%	130	309
Dimethylformamide (DMF)	68-12-2	Liquid	99%	>480	>480
Ethyl Acetate	141-78-6	Liquid	99%	>480	>480
Gasoline	Various	Liquid	Mixture	138	>480
Hydroflouric Acid	7664-39-3	Liquid	48%	>480	>480
n-Hexane	110-54-3	Liquid	99%	>480	>480
Methanol	67-56-1	Liquid	99%	25	33
Nitrobenzene	98-95-3	Liquid	99%	>480	>480
Sodium Hydroxide, 50%	1310-73-2	Liquid	50%	>480	>480
Sulfuric Acid 93.1% 66°B	7664-93-9	Liquid	93%	>480	>480
Tetrachloroethylene (perc)	127-18-4	Liquid	99%	>480	>480
Tetrahydrofuran (THF)	109-99-9	Liquid	99%	13	21
Toluene	108-88-3	Liquid	99%	>480	>480
Gases					
Ammonia Anhydrous	7664-41-7	Gas	99%	>480	>480
1, 3-Butadiene inhibit- ed 99%	106-99-0	Gas	99%	>480	>480
Chlorine 99.5%	7782-50-5	Gas	99%	>480	>480
Ethylene Oxide 99.7%	75-21-8	Gas	99%	>480	>480
Hydrogen Chloride 99%	7647-01-0	Gas	99%	182	>480
Methyl Chloride 99.5%	74-87-3	Gas	99%	>480	>480

 Methyl Chloride 99.5%
 74-87-3
 Gas
 99%
 >480

 Note: Chemical Resistance Data is in accordance with ASTM F739 test method. Testing is performed on fabric samples only, not finished garments. Sources for all test data are independent laboratories. All tests were performed under laboratory conditions and not actual use conditions.

Pyrolon[®] CB-FR Predicted Body Burn when worn over a Lakeland[®] 6.5 oz. Westex[®] DH FR Coverall (includes the head)

6.5 oz. Westex® DH coverall alone – 16.4% Total Body Burn

Burn	2nd Degree	3rd Degree	Average
Garment 1	0%	6.56%	6.56%
Garment 2	0.82%	6.56%	7.38%
Garment 3	2.46%	6.56%	9.02%
Overall Average			7.65%